

OK Autrod 12.32

Copper-coated, unalloyed wire for Submerged Arc and Electroslag Welding. Increased Si content and thus especially suitable for neutral fluxes (e.g.: OK Flux 10.62) or in order to increase the fluidity of the molten pool. With OK Flux 10.62 excellent toughness values; CTOD tested. For structural steels, ship building steels, pressure vessel steels, fine grained steels, off-shore constructions, etc.

Clasificaciones electrodo de hilo	SFA/AWS A5.17 : EH12K EN ISO 14171-A : S3Si
Aprobaciones	CE EN 13479 DB 52.039.12 VdTUV 12103 NAKS/HAKC 2.0 3.0 4.0 5.0 mm

Las aprobaciones dependen de la ubicación de la fábrica. Póngase en contacto con ESAB para obtener más información.

à% Composición hilo (valores típicos)

C	Mn	Si
0.13	1.77	0.30